

07-14-00

A

LAW OFFICES  
**WADDEY & PATTERSON**

A PROFESSIONAL CORPORATION  
SUITE 2020, BANK OF AMERICA PLAZA  
414 UNION STREET  
NASHVILLE, TENNESSEE 37219  
615-242-2400  
FAX 615-242-2221  
www.iplawgroup.com

PATENTS, TRADEMARKS,  
COPYRIGHTS, TRADE SECRETS,  
UNFAIR COMPETITION,  
COMPUTER LAW, LICENSING  
AND RELATED LITIGATION

ALABAMA OFFICE  
SUITE 302, AINSWORTH CENTER  
200 CLINTON AVENUE  
P O BOX 18485  
HUNTSVILLE, ALABAMA 35894  
256-535-4400  
FAX 256-535-4402

MARK J. PATTERSON  
I.C. WADDEY, JR.  
EDWARD D. LANQUIST, JR.  
LUCIAN WAYNE BEAVERS  
JOHN C. GARVIN, JR.\*  
LAURA K. THOMAS  
EMILY A. SHOUSE  
DAVID B. PIEPER  
LARRY W. BRANTLEY\*  
RICHARD S. MYERS, JR.\*

REGISTERED PATENT AGENTS

HAROLD W. HILTON  
MICHAEL J. MCCARTHY, PH.D.

TECHNICAL ADVISOR

DOUGLAS W. SCHELLING, PH.D.

\*LICENSED IN A STATE  
OTHER THAN TENNESSEE

July 13, 2000

Writer's Direct E-mail Address:  
rsm@iplawgroup.com

Assistant Commissioner for Patents  
Box New Patent Application  
Washington, DC 20231

**VIA EXPRESS MAIL LABEL**  
**NUMBER EL603384632US**  
**ATTORNEY'S DOCKET NO.: N-6089RSM**  
**Customer No.: 23456**

Dear Sir:

Enclosed for filing is the following:

1. Original utility patent application for the invention by Thomas L. Meredith of a "Composite Bone Material Implant and Prosthesis" which includes:
  - a. specification consisting of 20 pages;
  - b. declaration and power of attorney of the inventor;
2. Original filing fee in the amount of \$453.00.
3. Statement Claiming Small Entity Status - Independent Inventor.
4. Self-addressed return post card.

You are authorized to charge any deficiency or credit any overpayment associated with the filing of this application to Deposit Account 23-0035.

Very truly yours,

**WADDEY & PATTERSON**

Richard S. Myers, Jr.  
Registration Number 42,022

RSM/las  
enclosures

"EXPRESS MAIL" mailing label number:

EL603384632US

Date of deposit:

July 13, 2000



I hereby certify that this correspondence, including the following:

1. Original utility patent application for the invention by Thomas L. Meredith of a "Composite Bone Material Implant and Prosthesis" which includes:
  - a. specification;
  - b. declaration and power of attorney of the inventor;
2. Original filing fee in the amount of \$453.00.
3. Statement Claiming Small Entity Status - Independent Inventors.
4. Self-addressed return post card.

is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 C.F.R.§1.10 on the date indicated above and is addressed to:

Assistant Commissioner for Patents  
Box New Patent Application  
Washington, DC 20231

Date:

July 13, 2000

Richard S. Myers, Jr.

Applicant or Patentee: Thomas L. Meredith  
Customer No. 23456 RSM

Attorney's Docket No. N-6089

For: COMPOSITE BONE MATERIAL IMPLANT AND PROSTHESIS

**VERIFIED STATEMENT (DECLARATION) CLAIMING SMALL ENTITY STATUS  
(37 C.F.R. 1.9 (f) & 1.27 (c)) - INDEPENDENT INVENTOR**

As a below named inventor, I hereby declare that I qualify as an independent inventor as defined in 37 C.F.R. 1.9(c) for purposes of paying reduced fees under section 41(a) and (b) of Title 35, United States Code, to the Patent and Trademark Office with regard to the invention entitled "Composite Bone Material Implant and Prosthesis" described in the specification filed herewith.


I have not assigned, granted, conveyed or licensed and am under no obligation under contract or law to assign, grant, convey or license, any rights to the invention to any person who could not be classified as an independent inventor under 37 C.F.R. 1.9(c) if that person made the invention, or to any concern which would not qualify as a small business concern under 37 C.F.R. 1.9(d) or a nonprofit organization under 37 C.F.R. 1.9(a).

Each person, concern or organization to which I have assigned, granted, conveyed, or licensed, or am under an obligation under contract or law to assign, grant, convey, or license any rights in the invention is listed below:

There are no such persons, concerns, or organizations.

I acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement to small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date at which status as a small entity is no longer appropriate. (37 C.F.R. 1.28(b))

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application, any patent issuing thereon, or any patent to which this verified statement is directed.

  
Thomas L. Meredith

  
Date

5

**UNITED STATES PATENT APPLICATION**  
**COMPOSITE BONE MATERIAL IMPLANT AND PROSTHESIS**

10

This is a Patent Application filed for the invention by Thomas L. Meredith,  
of a "Composite Bone Material Implant and Prosthesis."

Field of the Invention

15

This invention generally relates to the field of bone composite implants  
and a method of forming bone composites. The composite is generally formed  
from a process comprising grinding bone tissue to form ground tissue, molding  
the ground bone tissue into a bone composite, and optionally applying a binder  
to the bone composite.

5

## 10

5

20

Processing of bone material which does not contain living tissue is becoming more and more important. Non-living bone grafting techniques have been attempted both for autografts and for allografts. For example, Nashef U.S. Patent No. 4,678,470 discloses a method of creating bone graft material by  
5 machining a block of bone to a particular shape or by pulverizing and milling it. The graft material is then tanned with glutaraldehyde to sterilize it. This process can produce bone plugs of a desired shape.

In the Nashef process, the process of pulverizing or milling the bone material destroys the structure of the bone tissue. The step of tanning it with  
10 glutaraldehyde then renders the graft material completely sterile.

It is now possible to obtain allograft bone which has been processed to remove all living material which could present a tissue rejection problem or an infection problem. Such processed material retains much of the mineral quality of the original living bone, rendering it more osteoinductive. Moreover,  
15 it can be shaped according to known and new methods to attain enhanced structural behavior. In fact spine surgeons express a distinct preference for such materials, and at least one supplier, the Musculoskeletal Transplant Foundation (MTF), has introduced femoral ring allografts for spine surgeries.

Research shows that such allografts are very favorable for spinal surgery.

20 According to Brantigan, J.W., Cunningham, B.W., Warden, K., McAfee, P.C.,

and Steffee, A.D., A compression Strength of Donor Bone for Posterior Lumbar Interbody Fusion, Spine, Vol. 18, No. 9, pp.12113-21 (July 1993):

Many authors have viewed donor bone as the equivalent of autologous bone. Nasca, et al. . . . compared spinal fusions in 62 patients with autologous bone and 90 patients with cryopreserved bone and found successful arthrodesis in 87% of autologous and 86.6% of allograft patients. (Citations omitted.).

A drawback of fabricating transplants and prostheses from donated allograft is that the process necessitates discard of a great deal of scrap and powdered bone material. Good quality donated bone is a scarce resource, so that devising a method of using scrap and powdered allograft bone material would be of great assistance to this highly beneficial endeavor. The present invention uses powdered bone to make solid shapes. The results of the present invention are superior to the prior art processes and the process and composite of the present invention allows for a greater amount of donor bone to become available. For example, with the present invention, bone can now be used from older donors. With a transplanted allograft, older bone may be too brittle and weak.

In the fabrication of bone transplants, it was observed that bone material which yields to compressive loads at the exterior surfaces without significant

degradation of the interior structural properties, such as cancellous or trabecular bone, can be shaped. It is not unusual that reshaping of a graft tissue is necessary to obtain the best possible graft. In particular, bone tissue may be stronger and better able to bear force when it is denser and more compact.

Additionally, prior art techniques have a serious limitation in that bone parts and bone products made from allograft cortical tissue may be limited in size, dimension and shape because of the anatomical limits on the thickness and length of the source bone. With the method of the present invention, many shapes and forms can be fabricated from allograft cortical bone tissue including pins, screws, plates, intervertebral discs, and the like for use in surgery.

Allograft bone occurs in two basic forms: cancellous bone (also referred to as trabecular bone) and cortical bone. Cortical bone is highly dense and has a compound structure comprised of calcium hydroxyapatite reinforced with collagen fiber. In the present invention, cortical bone tissue is preferred.

Compression of allograft bone is desirable from general considerations. Generally, bone samples are stronger when they are more dense. Compressing allograft bone increases its density and thus generally strengthens the allograft. In addition, recent studies have indicated that the shell of vertebral



bone is very much like condensed trabecular bone. Mosekilde, L., A Vertebral structure and strength in vivo and in vitro, Calc. Tissue Int. 1993;53 (Suppl) :121-6; Silva, M.J., Wang, C., Keaveny, T.M., and Hayes, W.C., A Direct and computed tomography thickness measurements of the human lumbar vertebral  
5 shell and endplate, Bone 1994:15:409-14; Vesterby, A., Mosekilde, L., Gunderson, H. J.G., et al., Biologically meaningful determinants of the in vitro strength of lumbar vertebrae, Bone 1991;12:219-24.

Compression also allows conversion of larger irregular shapes into the desirable smaller shape, thereby permitting more disparate sources of allograft  
10 bone to be used. By compressing bone to a given shape it is possible to configure the allograft to match a preformed donee site prepared by using a shaped cutter to cut a precisely matching cut space. In particular, this method of formation facilitates the formation of match mated surfaces of the implant for the formation of a particular shape for skeletal repair or revision.

15 For the reasons stated above, in certain embodiments of the present invention, compression is useful as part of the molding step in forming the bone composites of the present invention.

It is known that allograft bone can be reshaped into one of many configurations for use as an implant. Various methods, including that of

Bonutti, U.S. Patents Nos. 5,662,710 and 5,545,222, can be used to shape allograft material into the desired shape.

A goal of a bone composite transplant is that the transplant is readily received and hosted by the receiving mammal, with bone fusion occurring (i.e., the composite should be biocompatible and osteoinductive). Today, the only other osteoinductive implants are allograft shapes that have been cut and shaped from cadaver donated bone. This method has serious drawbacks in that it is difficult for sufficient fusion to take place and the implant usually lacks sufficient structural strength and density.

U.S. Patent No. 6,025,538 to Yaccarino, III, discloses allograft bone devices for surgical implantation in the bone tissue.

U.S. Patent No. 5,439,864 to Pruitt, et al., discloses shaped demineralized bone for use in the surgical repair of bone defects.

U.S. Patent No. 5,662,710 to Bonutti, discloses a tissue press for shaping or compressing a piece of graft tissue.

In response to the need for a composite material to make use of bone fragments and bone powder for fabricating implants and prosthetic devices for bone the current inventor developed the present invention.

Summary of the Invention

It is an object of the present invention to provide a bone composite that is readily received and hosted when received by another mammal. When successful, bone fusion occurs, and the biocompatible and osteoinductive process allows the body to lay down native bone in combination with the implanted bone composite.

The present invention relates to a method of forming a bone composite, comprising: providing bone tissue; grinding said bone tissue to form ground tissue; molding the ground bone tissue into a bone composite; optionally applying a binder to the bone composite; and optionally milling or refining the bone composite to the desired shape. Preferably, the bone tissue is substantially cortical bone tissue (i.e., greater than about 40-50%), and preferably, the bone tissue is substantially demineralized.

More preferably, the bone tissue is greater than about 50% cortical bone tissue, more preferably in the range of greater than about 50-70% cortical bone tissue, more preferably in the range of greater than about 50-90% cortical bone tissue, more preferably in the range of greater than about 50-95% cortical bone tissue, more preferably 90% cortical bone tissue, and more preferably greater than about 95% cortical bone tissue. The size of the ground bone particles can vary, but typically the particles will range in size from 125 to 850 microns in size.

The above-mentioned occurs at from 14.7 psi to about 30,000 psi.

The binder may be a cyanoacrylate and/or fibrin and is applied to the bone composite either before or after the molding step, preferably by injection, spray, or bath methods.

The present invention also encompasses bone tissue composites made therefrom. The composites may be, for example, a bone pin, screw, or prosthesis.

#### Detailed Description of the Preferred Embodiments

The method and composite of the present invention can be used with any mammal, preferably horses and humans, most preferably humans. However, it is preferred that donor bone is the same species as recipient bone. That is, preferably human bone is used in making a bone composite that will be used by a human. Preferably the bone tissue is demineralized.

As stated above, preferably cortical bone tissue is used to form the composites of the present invention. More preferably, the composites are substantially cortical bone tissue, preferably above 50% cortical bone tissue, more preferably the bone tissue is greater than about 70%, 90%, or greater than about 95% cortical bone tissue.

Bone powder is placed in a mold and compressed using compression tooling. Then a form of adhesive is applied to the bone powder and permitted

to set. The composite bone blank, implant, or prosthesis is then removed from the mold and processed by machining and/or other surface preparation.

The type of mammalian bone that is most plentiful and most preferred as a resource for the composites of the present invention is cortical bone, which is also the form of bone tissue with the greatest compressive strength. Pulverized bone can be collected and separated into a number of batches, each batch comprising a different mean particle size. The particle size can vary from fine to coarse. The properties of the composite to be produced can be tailored by choice of particle size. For example, particles in the range of from about 125 to about 850 microns can be used for making bone composites useful for skeletal repair and revision.

In addition, pressure during formation can be tailored to the desired outcome. The pressure used in embodiments of the present invention can range from 14.7 to 30,000 psi. Lower pressures (i.e., from atmospheric to 15,000 psi) can be used to form bone composites useful for skeletal repair and revision. Higher pressures (i.e., from about 15,000 psi to about 30,000 psi) can be used to form bone composites useful for applications such as a bone screw.

The binder, when present, is added in an amount to sufficiently provides a cohesive ground bone composite that can be used in skeletal repair and

revisions methods without the ground bone coming apart. Preferably, the binder is present in an amount from .025mL to 10.0mL weight/volume. More preferably, the binder is present in an amount of from about 5% to about 50% of volume. Additionally, the particular binder used can be varied according to  
5 desired properties. For example, cyanoacrylates can be used as a binder in the production of cortical onlay plates and is preferably present in amount of from 20% to 30%. A binder may also be combined with at least one other binder. The binder is applied by injection, spray, bath, soaking or layering.

The above general ranges allow one of ordinary skill in the art to create a  
10 composite of proper density and mechanical properties and further allows the same basic device to be tailored to individual patients and situations.

As stated above, the preferred binder is a biocompatible cyanoacrylate. Preferred biocompatible cyanoacrylates include ester chain, N-butyl, and butyl cyanoacrylates.

15 In addition to cyanoacrylates, at least one other adhesive substance can optionally be used as a matrix to form composite bone material (in combination with or without at least one cyanoacrylate). For example, fibrin is a substance formed by human blood when it clots. Fibrin bonds the platelets together in the formation of, e.g., clots and scabs. Alternatively, fibrin glue can be  
20 manufactured. Other biocompatible adhesives can also be used. In addition,

there exist a number of biocompatible gels which can be used as a matrix adhesive for holding bone powder together to form a composite.

The following examples are intended to be for illustrative purposes and do not limit the spirit and scope of the present invention.

#### Example 1

5 This example discusses a process of the present invention for making a bone composite disc at atmospheric pressure. Pre-ground cortical bone is sieved to a range of from 125-850 microns. Sieved bone is then measured to a volume of 75% of desired disc size (volume). A polyethylene mold cored in the  
10 shape of  $\frac{1}{2}$  inch diameter by  $\frac{1}{4}$  inch cylinder is then filled with 75% sieved bone, or .0368 cu/in. There is a polyethylene sized  $\frac{1}{2}$  inch by 1 inch plug at the base of the cored mold cylinder shape. This is used to eject cured bone disc. The bone particles are then slightly hydrated with a sterile water spray at greater than 1%. Cyanoacrylate measured at 25% of  $\frac{1}{2}$  inch by  $\frac{1}{4}$  inch core  
15 volume, or 0.0123 cu/in is then poured into ground bone volume and allowed to wick for three minutes. The newly formed bone disc is then allowed to cure for a period of one hour at 14.7 p.s.i. After one hour, the mold ejection pin is pushed manually upward from base of mold, allowing the hard-set bone disc to be removed. Bone disc is then inspected for any out of tolerance measurement  
20 as well as shape. If trim is necessary, it may take place at this time.

## Example 2

002720-01991960  
This example discusses a process of the present invention for making a bone composite screw with external high pressure. A specially designed high-pressure vessel is used. The design is two die plates which have been modeled  
5 in the shape of a  $\frac{1}{4}$  inch diameter by 1 inch long screw. Each plate is half of one screw. Plates are made of high carbon stainless steel and through hardened. Multiple high tensile socket head cap screws are also used to hold die plates in place. A pneumatic over water high-pressure intensifier (pump) with the ability to generate 250,000 pounds of force is used. This pump is  
10 machined with  $\frac{1}{4}$  inch high-pressure ports that are adaptable with high pressure fittings and tubing. Pre-ground cortical bone is sieved to a range of 125-180 microns. Sieved bone is then measured to a volume of 200% desired screw size and placed into a pressure vessel. The pressure vessel with ground bone is then placed into a special high-pressure polycarbonate (explosion proof)  
15 safety box and pressure is then applied. Pneumatic pressure is slowly regulated upward until a water gauge pressure of 15,000 p.s.i. is reached at cylinder squeeze side of the pressure vessel. Pressure is held for a period of one hour resulting with a force of 124,500 pounds at the bone screw. This amount of force is the result of 15,000 p.s.i. being subjected to the face of  $3 \frac{1}{4}$   
20 bore cylinder diameter (where pressure x area = force). Actual bone screw density will increase with original bone volume squeezing from 200% down to



75%, which is near actual size of finished bone screw (greater than 5%). Pressure is released from pressure vessel and socket head cap screws are backed out. At this time, the bone screw may be manually removed from the die. The bone screw is hydrated with a light water spray and sterile water is  
5 allowed to wick into the bone screw for a period of three minutes. Gently, the bone screw may be bathed (dipped) into a cyanoacrylate pool and allowed to wick cyanoacrylate for about 10 seconds. The bone screw is then allowed to cure for a period of one hour, after which it may inspected for density, outside envelope dimensions and shape. The bone screw may now be implanted for  
10 skeletal repair and/or revision.

All patents, journal articles, and other publications cited in this disclosure are hereby expressly incorporated by reference.

From the foregoing description of the present invention, those skilled in the art will perceive improvements, changes and modifications, and understand  
15 that the specific details shown herein are merely illustrative. Such changes, modifications, and improvements do not depart from the spirit and scope of the following claims.

We claim:

1. A method of forming a bone composite, comprising:

5 providing bone tissue;

grinding said bone tissue to form ground bone tissue;

molding the ground bone tissue into a bone composite;

optionally applying a binder to the bone composite;

optionally milling or refining the bone composite to the desired shape.

10 2. The method of claim 1, wherein the bone tissue is substantially cortical bone tissue.

15 3. The method of claim 2, wherein the bone tissue is substantially demineralized.

4. The method of claim 2, wherein the bone tissue is greater than 50% cortical bone tissue.

20 5. The method of claim 2, wherein the bone tissue is greater than 70% cortical bone tissue.

6. The method of claim 1, wherein the ground bone tissue is greater than 90% cortical bone tissue.

7. The method of claim 1, wherein the ground bone tissue is greater than  
5 95% cortical bone tissue.

8. The method of claim 1, wherein the ground bone tissue is from 125 to 850 microns in size.

10 9. The method of claim 1, wherein the molding step occurs at from 14.7 p.s.i. to about 30,000 p.s.i.

10. The method of claim 1, wherein the binder is applied to the ground bone before the molding step.

15 11. The method of claim 1, where the binder is applied to the ground bone after the molding step.

12. The method of claim 1, wherein the binder is applied by an injection,  
20 spray, bath, soaking or layering.

13. The method of claim 1, wherein the binder comprises fibrin.

14. The method of claim 1, wherein the binder comprises cyanoacrylates.

15. The method of claim 12, wherein the cyanoacrylates comprise ester  
5 chain, N-butyl, or butyl cyanoacrylates.

16. The method of claim 12, wherein the cyanoacrylates are long chain  
cyanoacrylates.

10 17. The method of claim 1, wherein the bone composite is a bone pin, screw  
or prosthesis.

18. The method of claim 1, wherein the molding step further comprises the  
application of pressure and shaping the composite with a die.

15 19. A bone tissue composite, comprising:  
ground bone tissue molded to form a desired shape; and  
a binder selected from at least one of a cyanoacrylate or fibrin.

20 20. The bone tissue composite of claim 19, wherein the bone tissue is  
substantially cortical bone tissue.

21. The bone tissue composite of claim 19, wherein the bone tissue is more than 50% cortical bone tissue.

22. The bone tissue composite of claim 19, wherein the bone tissue is more  
5 than 70% cortical bone tissue.

23. The bone tissue composite of claim 19, wherein the bone tissue is more than 90% cortical bone tissue.

10 24. The bone tissue composite of claim 19, wherein the bone tissue is more than 95% cortical bone tissue.

25. The bone tissue composite of claim 19, wherein the ground bone tissue is from 125 to 850 microns in size.

15 26. The bone tissue composite of claim 19, wherein the desired shape is molded at from 14.7 psi to about 30,000 psi.

27. The bone tissue composite of claim 19, wherein the binder comprises  
20 fibrin.

28. The bone tissue composite of claim 19, wherein the binder comprises cyanoacrylates.

29. The bone tissue composite of claim 19, wherein the cyanoacrylates  
5 comprise ester chain, N-butyl, or butyl cyanoacrylates.

30. The bone tissue composite of claim 19, wherein the cyanoacrylates are long chain cyanoacrylates.

10 31. The bone tissue composite of claim 19, wherein the bone composite is a bone pin, screw or prosthesis.

32. A method of forming a bone composite, comprising:  
providing bone tissue,  
15 grinding said bone tissue to a size of from 125 to 850 microns in size to form ground bone tissue,  
molding the ground bone tissue under pressure to form a bone composite,  
introducing a cyanoacrylate binder to the bone composite.

Abstract of the Disclosure

The present invention relates to a method of forming a bone composite, comprising: providing bone tissue; grinding said bone tissue to form ground tissue; molding the ground bone tissue into a bone composite; optionally  
5 applying a binder to the bone composite; and optionally milling or refining the bone composite to the desired shape. The present invention also encompasses bone tissue composites made therefrom. The composites may be, for example, a bone pin , screw, or prosthesis.

## DECLARATION AND POWER OF ATTORNEY

As the below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name; that

I believe I am the original, first and sole inventor of the invention entitled "Composite Bone Material Implant and Prosthesis" described and claimed in the attached specification.

I have reviewed and understand the contents of the specification, including the claims, in the above-referenced application, as amended by any amendment specifically referred to in the Declaration.

I acknowledge my duty pursuant to 37 C.F.R. §1.56 to disclose information of which I am aware which is material to the patentability of this application.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate



listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

None.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

I hereby appoint the following attorneys to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

Mark J. Patterson (Reg. No. 30,412)  
I. C. Waddey, Jr. (Reg. No. 25,180)  
Edward D. Lanquist, Jr. (Reg. No. 33,729)  
Lucian Wayne Beavers (Reg. No. 28,183)  
John C. Garvin, Jr. (Reg. No. 20,542)  
Laura K. Thomas (Reg. No. 39,856)  
Emily A. Shouse (Reg. No. 44,336)  
David B. Pieper (Reg. No. 42,998)  
Richard S. Myers, Jr. (Reg. No. 42,022)  
Larry W. Brantley (Reg. No. P-46,052)

414 Union Street, Suite 2020  
Bank of America Plaza  
Nashville, TN 37219  
(615) 242-2400

Address all telephone calls to Richard S. Myers, Jr. at telephone number (615) 242-2400.


Address all correspondence to:

Richard S. Myers, Jr.  
Wadley & Patterson  
414 Union Street, Suite 2020  
Bank of America Plaza  
Nashville, TN 37219  
Customer No. 23456

Full name of Inventor:

Thomas L. Meredith

Inventor's signature:



July 12, 2000  
Date

Residence:

6524 Banbury Crossing  
Brentwood, TN 37027

Citizenship:

United States

Post Office Address:

6524 Banbury Crossing  
Brentwood, TN 37027

006720-01991960